



CL – BITUMEN PRIMER

SOLVENT BASED PRIMER FOR BITUMINOUS WATERPROOFING SYSTEM

DESCRIPTION

CL-BITUMEN PRIMER is a solvent based bituminous solution designed to penetrate and seal the pores of mineral surfaces and promote the adhesion of the substrate prior to the application of a bituminous waterproofing system.

USES

Can be applied on many substrates including metal, slate, concrete, asbestos, cement, lightweight concrete, cement screed and the like.

FEATURES

- Fast dry
- Ready to use
- Economical
- Good penetration
- Excellent adhesion

TECHNICAL INFORMATION

Appearance	: Black liquid
Specific Gravity @ 28°C	: Approx. 0.87
Drying Time @ 30°C	: 2 - 4 hours depending on climatic condition
Flash Point	: $\geq 32^{\circ}\text{C}$
Solid Content	: Approx. 40%

COVERAGE

- Non-absorbent surface : 12 - 16m²/litre
- Absorbent surface : 6 - 8m²/litre
- Highly absorbent surface : 3 - 4m²/litre

SURFACE PREPARATION

Surfaces to be coated must be dry and clean; free from dust, dirt, grease, moss and loose particles. Fresh concrete must be cured for at least 14 days prior to the application.

APPLICATION

Use brush or roller. Do not dilute. Apply onto the substrate as per recommended rate. Allowed it to dry completely prior to waterproofing application. Drying time may vary from 2 - 4 hours depending on weather condition. Incomplete drying of primer may give rise to de-bonding problem between interface of primer and waterproofing system.

PRECAUTION MEASURES

Flammable! Precaution needs to be taken while handling. Keep away from sparks, naked flame or any heat sources.

TOOLS CLEANING

Tools can be cleaned with kerosene or general purpose thinner.

SHELF LIFE

2 years when stored in cool and dry place, sealed in unopened container.

PACKING

Available in 18 litres tin and 205 litres drum.

122001

Disclaimer: Specification are subject to change without notification.

CLP since 1947
HQ/SINGAPORE : CLP INTERNATIONAL PTE LTD
CHIN LEONG CONSTRUCTION SYSTEMS PTE LTD
TEL : +65-6265 2788
FAX : +65-6265 1240
Email : chinleong@clp.com.sg

MALAYSIA: CLP CONSTRUCTION SYSTEMS SDN BHD
SELANGOR
TEL : +60-3-3176 5099
FAX : +60-3-3176 2797
Email : clp@clp.com.my
MALACCA
TEL : +60-6-263 1677
FAX : +60-6-263 1215

JOHOR
TEL : +60-7-252 5385
FAX : +60-7-252 5391

KEDAH
TEL : +60-4-489 3066
Fax : +60-4-489 1877

PERAK
TEL : +60-5-292 6986 / 6976
FAX : +60-5-292 6936

INDONESIA :
PT RANGALO CLP
TEL : +62-21-581 3951
FAX : +62-21-581 3950
Email : rangalo@cbn.net.id

PT-CLP INDONESIA
ZHONG SHAN
TEL : +62-21-2931 5121
FAX : +62-21-2931 5133 / 28
Email : info@clpindo.com

THAILAND:
CLPI (THAILAND) CO LTD
TEL : +66-2769 5633
FAX : +66-2769 5612
Email : clpi@ksc.th.com

VIETNAM :
CLPI VIETNAM CO LTD
TEL : +84-8-3526 1033
FAX : +84-8-3526 1032
Email : sales@clp.com.vn

TAIWAN :
SIHTACO CO LTD
TEL : +886-2-2791 8539
FAX : +886-2-8192 6248
Email : Alice.Lee@sihtaco.com.tw
Michael.Ku@sihtaco.com.tw

HONG KONG :
CHIN LEONG INTERNATIONAL CO LTD
LAMERTON ASIA HOLDING LTD
TEL : +852-2542 2206
FAX : +852-2544 9563
Email : chinleong@chinleong.com.hk

CHINA:
LAMERTON CHEMICAL (SHANGHAI) CO LTD
SHANGHAI
TEL : +86-21-5830 7559
FAX : +86-21-6840 7408

ZHONG SHAN SOUTH ASIA CHEMICAL LTD
ZHONG SHAN
TEL : +86-760-8554 4111
FAX : +86-760-8554 4113