



# CL – BOND FLEX 2 IN 1

PREMIUM CEMENTITIOUS TILE ADHESIVE (GREY)

## DESCRIPTION

**CL-BOND FLEX 2 IN 1** is a premium grey coloured premixed dry set cementitious adhesive of superior quality, suitable for interior and/or exterior fixing of absorptive and non-absorptive wall and floor tiles / marble. CL-Bond Flex 2in1 contains high performance specialty grade polymer and does not require additional latex admixture to enhance its performance.

## FIXES

- Marble / Granite
- Porcelain / Homogenous / Ceramic / Mosaics tiles
- Stones materials and others

## FEATURES

- No additional latex admixture is required
- Superior bonding strength
- Excellent workability
- Durable
- Water resistant
- Ready to use

## TEST CERTIFICATES

- Sirim Malaysia

## TECHNICAL INFORMATION

Classification	: C2TE
Initial Tensile Adhesion Strength (BS EN 12004-2:2017)	: $\geq 2 \text{ N/mm}^2$ @ 28day
Working Time	: 40 – 60 min depending climatic conditions
Initial Set Time	: 9 – 10 hrs
Final Set Time	: 10 – 12 hrs

## MIXING

Use clean and potable water for mixing. Mix in the proportion of 20kg of CL-Bond Flex 2in1 with 5.75 – 6.0 litre of water. Add adhesive to water and mix thoroughly until a slump-free mix is obtained. Let it stand for 5 minutes, then remix. After slaking period, do not add water or other ingredients. During use, remix occasionally.

For wet areas as well as water submerged areas such as swimming pools, CL-Bond Flex 2in1 can be used with CL-Flex 303 to enhance the water resistance requirement.

## SPREADING THE MIX

Prior to spreading the mix, do not soak marble or tile backing surface. Dampen dry backing only to achieve cure.

Do not spread the mix to surface that contains frost. It should be floated with pressure over an area not greater than can be covered with marble / tile while the mix remained plastic.

Spread the mix on the surface using a notched trowel to a depth of 5-6mm at approximately 1 – 2 sq. meter at one time. Comb with the notched trowel to obtain continuous horizontal ribs of adhesive. Ensure that the adhesive is wet when tiles are laid.

## INSTALLATING TILE

Immediately press tile freshly combed adhesive. To obtain adequate contact between tile and adhesive bed, tap and beat the tile so that no void occur within the adhesive.

For rib back tile, trowel a layer of adhesive on the back of tile to obtain full contact prior to placing the tile on the adhesive bed.

Do not place tile on adhesive bed that had been set, remove and discard old adhesive. Tapping and wetting of the tile will not provide bonding of adhesive that had been set too long.

## GROUTING

Do not grout until tile is firmly set and restrict all traffic and other works for a minimum of 24 hours on floor installation.

## COVERAGE

Approximately 3 kg per sq m on a 3 mm bed. Recommended thickness is 3 – 8mm depending on tile size.

## SHELF LIFE

12 months in unopened bag, stored in cool and dry place.

## PACKING

Available in 20 kg bag.

022513

Disclaimer: Specification are subject to change without notification.



CLP since 1947  
HQ/SINGAPORE : CLP INTERNATIONAL PTE LTD  
CHIN LEONG CONSTRUCTION SYSTEMS PTE LTD  
TEL : +65-6265 2788  
FAX : +65-6265 1240  
Email : chinleong@clp.com.sg

MALAYSIA: CLP CONSTRUCTION SYSTEMS SDN BHD  
SELANGOR  
TEL : +60-3-3176 5099  
FAX : +60-3-3176 2797  
Email : clp@clp.com.my

MALACCA

TEL : +60-6-225 0540

FAX : +60-6-263 1677

JOHOR

TEL : +60-7-252 5385

FAX : +60-7-252 5391

KEDAH

TEL : +60-4-489 3066

Fax : +60-4-489 1877

PERAK

TEL : +60-5-292 6986 / 6976

FAX : +60-5-292 6936

INDONESIA :

PT RANGALO CLP

TEL : +62-21-581 3951

FAX : +62-21-581 3950  
Email : rangalo@cbln.net.id

PT-CLP INDONESIA

TEL : +62-21-2931 5121

FAX : +62-21-2931 5133 / 28  
Email : info@clpindo.com

THAILAND:  
CLPI (THAILAND) CO LTD  
TEL : +66-2769 5633  
FAX : +66-2769 5612  
Email : clpi@ksc.th.com

VIETNAM :  
CLPI VIETNAM CO LTD  
TEL : +84-8-3526 1033  
FAX : +84-8-3526 1032  
Email : sales@clp.com.vn

TAIWAN :  
SIHTACO CO LTD  
TEL : +886-2-2791 8539  
FAX : +886-2-8192 6248  
Email : Alice.Lee@sihtaco.com.tw  
Michael.Ku@sihtaco.com.tw

HONG KONG :  
CHIN LEONG INTERNATIONAL CO LTD  
LAMERTON ASIA HOLDING LTD  
TEL : +852-2542 2206  
FAX : +852-2544 9563  
Email : chinleong@chinleong.com.hk

CHINA:  
LAMERTON CHEMICAL (SHANGHAI) CO LTD  
SHANGHAI  
TEL : +86-21-5830 7559  
FAX : +86-21-6840 7408

ZHONG SHAN SOUTH ASIA CHEMICAL LTD  
ZHONG SHAN  
TEL : +86-760-8554 4111  
FAX : +86-760-8554 4113