



# CL – BOND G8T / W3T

## THICK BED ADHESIVE FOR MARBLE / GRANITE/ LARGE TILE

### DESCRIPTION

**CL-BOND G8T / W3T** is a grey / white coloured premixed dry set cementitious adhesive with high strength aggregate, formulated specially for thick bed installation of marbles, granite and large tiles. For interior / exterior fixing of absorptive and non-absorptive marbles, granite and large tiles with thickness of 5 to 15mm.

### FIXES

Can be used for Marbles, Granites, Terrazo, Homogeneous Tiles, Ceramic and others. CL-Bond W3T is recommended for the installation of light coloured stones to prevent “shadowing”.

### TECHNICAL INFORMATION

Classification	: C2E
Initial Tensile Adhesion Strength (BS EN 12004-2:2017)	: $\geq 1\text{N/mm}^2$ @ 28 day
Working Time	: 20 – 30 minutes depending
Initial Set Time	: 3 – 6 hrs
Final Set Time	: 4 – 8 hrs

### MIXING

Use clean and potable water for mixing. Mix in the proportion of 25kg of CL-Bond G8T / W3T with 4.5 litre of water. Add adhesive to water and mix thoroughly until a slump-free mix is obtained. Let it stand for 5 minutes, then remix. After slaking period, do not add water or other ingredients. During use, remix occasionally.

Alternatively, CL-Bond G8T / W3T can be used in conjunction with CN-Flex 1000 latex admixture to enhance and increase flexural, bonding and shear strengths where critical application is required, especially when installing on the wall.

For wet areas as well as water submerged areas such as swimming pools, CL-Bond G8T / W3T can be used with CL-Flex 303 to enhance the water resistance requirement.

### SPREADING THE MIX

Prior to spreading the mix, do not soak marble or tile backing surface. Dampen dry backing only to achieve cure.

Do not spread the mix to surface that contains frost. It should be floated with pressure over an area not greater than can be covered with marble / tile while the mix remained plastic.

Spread the mix on the surface using a notched trowel to a depth of 10 - 30mm at approximately 1 – 2 sq. meter at one time. Comb adhesive with the notched trowel to obtain continuous horizontal ribs of adhesive. Ensure that the adhesive is wet when tiles are laid.

### INSTALLATING TILE

Immediately press tile freshly combed adhesive. To obtain adequate contact between tile and adhesive bed, tap and beat the tile so that no void occur within the adhesive.

For rib back tile, trowel a layer of adhesive on the back of tile to obtain full contact prior to placing the tile on the adhesive bed.

Do not place tile on adhesive bed that had been set, remove and discard old adhesive. Tapping and wetting of the tile will not provide bonding of adhesive that had been set too long.

### GROUTING

Do not grout until tile is firmly set and restrict all traffic and other works for a minimum of 24 hours on floor installation.

### COVERAGE

Approximately 7 kg per sq m on a 5 mm bed.

### SHELF LIFE

12 months in unopened bag, stored in cool and dry place.

### PACKING

Available in 25kg bag.

022513

Disclaimer: Specification are subject to change without notification.

 CLP since 1947  
HQ/SINGAPORE : CLP INTERNATIONAL PTE LTD  
CHIN LEONG CONSTRUCTION SYSTEMS PTE LTD  
TEL : +65-6265 2788  
FAX : +65-6265 1240  
Email : chinleong@clp.com.sg

**MALAYSIA: CLP CONSTRUCTION SYSTEMS SDN BHD**  
**SELANGOR** TEL : +60-3-3176 5099  
FAX : +60-3-3176 2797  
Email : clp@clp.com.my  
**MALACCA** TEL : +60-6-263 1677 /  
+60-6-225 0540

**JOHOR**  
TEL : +60-7-252 6385  
FAX : +60-7-252 5391

**KEDAH**  
TEL : +60-4-489 3066  
Fax : +60-4-489 1877

**PERAK**  
TEL : +60-5-292 6986 / 6976  
FAX : +60-5-292 6936

**INDONESIA :**  
**PT RANGALO CLP**  
TEL : +62-21-581 3051  
FAX : +62-21-581 3950  
Email : rangalo@cbn.net.id

**PT-CLP INDONESIA**  
TEL : +62-21-2831 5121  
FAX : +62-21-2831 5133 / 28  
Email : info@clpindo.com

**THAILAND:**  
**CLPI (THAILAND) CO LTD**  
TEL : +66-2769 5633  
FAX : +66-2769 5612  
Email : clpi@ksc.th.com

**VIETNAM :**  
**CLPI VIETNAM CO LTD**  
TEL : +84-8-3526 1033  
FAX : +84-8-3526 1032  
Email : sales@clp.com.vn

**TAIWAN :**  
**SIHTACO CO LTD**  
TEL : +886-2-2791 8539  
FAX : +886-2-8192 6248  
Email : Alice.Lee@sihtaco.com.tw  
Michael.Ku@sihtaco.com.tw

**HONG KONG :**  
**CHIN LEONG INTERNATIONAL CO LTD**  
**LAMERTON ASIA HOLDING LTD**  
TEL : +852-2542 2206  
FAX : +852-2544 9563  
Email : chinleong@chinleong.com.hk

**CHINA:**  
**LAMERTON CHEMICAL (SHANGHAI) CO LTD**  
**SHANGHAI**  
TEL : +86-21-5830 7559  
FAX : +86-21-6840 7408

**ZHONG SHAN SOUTH ASIA CHEMICAL LTD**  
**ZHONG SHAN**  
TEL : +86-760-8554 4111  
FAX : +86-760-8554 4113