



CL – BOND W3

CEMENTITIOUS TILE ADHESIVE (WHITE)

DESCRIPTION

CL-BOND W3 is a white coloured premixed dry set cementitious adhesive with high bonding strength, formulated specially for interior and / or exterior fixing of light coloured absorptive and non-absorptive marble / wall and floor tiles to eliminate “shadowing”.

FIXES

- Marble / Granite
- Porcelain / Homogenous / Ceramic / Mosaics tiles
- Stones materials and others

FEATURES

- Superior bonding strength
- Good workability
- Durable
- Ready to use

TEST CERTIFICATES

- TUV PSB Singapore
- Sirim Malaysia
- Singapore Green Building Council ✓✓✓ Excellent

TECHNICAL INFORMATION

Classification	: C2TE
Initial Tensile Adhesion Strength	: $\geq 1.5\text{N/mm}^2$ @ 28 day (BS EN 12004-2:2017)
Working Time	: 20 – 30 min depending on climatic conditions
Initial Set Time	: 3 – 5 hrs
Final Set Time	: 4 – 8 hrs

MIXING

Use clean and potable water for mixing. Mix in the proportion of 20kg of CL-Bond W3 with 5.25 – 5.5 litre of water. Add adhesive to water and mix thoroughly until a slump-free mix is obtained. Let it stand for 5 minutes, then remix. After slaking period, do not add water or other ingredients. During use, remix occasionally.

Alternatively, CL-Bond W3 can be used in conjunction with CN-Flex 1000 latex admixture to enhance and increase flexural, bonding and shear strengths where critical application is required, especially when installing on the wall.

For wet areas as well as water submerged areas such as swimming pools, CL-Bond W3 can be used with CL-Flex 303 to enhance the water resistance requirement.

SPREADING THE MIX

Prior to spreading the mix, do not soak marble or tile backing surface. Dampen dry backing only to achieve cure.

Do not spread the mix to surface that contains frost. It should be floated with pressure over an area not greater than can be covered with marble / tile while the mix remained plastic.

Spread the mix on the surface using a notched trowel to a depth of 5-6mm at approximately 1 – 2 sq. meter at one time. Comb with the notched trowel to obtain continuous horizontal ribs of adhesive. Ensure that the adhesive is wet when tiles are laid.

INSTALLATING TILE

Immediately press tile freshly combed adhesive. To obtain adequate contact between tile and adhesive bed, tap and beat the tile so that no void occur within the adhesive.

For rib back tile, trowel a layer of adhesive on the back of tile to obtain full contact prior to placing the tile on the adhesive bed.

Do not place tile on adhesive bed that had been set, remove and discard old adhesive. Tapping and wetting of the tile will not provide bonding of adhesive that had been set too long.

GROUTING

Do not grout until tile is firmly set and restrict all traffic and other works for a minimum of 24 hours on floor installation.

COVERAGE

Approximately 3 kg per sq m on a 3 mm bed. Recommended thickness is 3 – 8mm depending on tile size.

SHELF LIFE

12 months in unopened bag, stored in cool and dry place.

PACKING

Available in 20 kg bag.

042508

Disclaimer: Specification are subject to change without notification.

 CLP since 1947 HQ/SINGAPORE : CLP INTERNATIONAL PTE LTD CHIN LEONG CONSTRUCTION SYSTEMS PTE LTD TEL : +65-6265 2788 FAX : +65-6265 1240 Email : clp@clp.com.sg	THAILAND: CLPI (THAILAND) CO LTD TEL : +66-2769 5633 FAX : +66-2769 5612 Email : clp@ksc.th.com	VIETNAM: CLPI VIETNAM CO LTD TEL : +84-8-3526 1033 FAX : +84-8-3526 1032 Email : sales@clp.com.vn	TAIWAN: SIHTACO CO LTD TEL : +886-2-2791 8539 FAX : +886-2-8192 6248 Email : Alice.Lee@sihtaco.com.tw Michael.Ku@sihtaco.com.tw	MALAYSIA: CLP CONSTRUCTION SYSTEMS SDN BHD SELANGOR TEL : +60-3-3176 5099 FAX : +60-3-3176 2797 Email : clp@clp.com.my	MALACCA TEL : +60-6-263 1677 / +60-6-225 0540	JOHOR TEL : +60-7-252 5385 FAX : +60-7-252 5391	KEDAH TEL : +60-4-489 3066 Fax : +60-4-489 1877	PERAK TEL : +60-5-292 6986 / 6976 FAX : +60-5-292 6936	INDONESIA : PT RANGALO CLP TEL : +62-21-581 3951 FAX : +62-21-581 3950 Email : rangalo@cbn.net.id	PT-CLP INDONESIA TEL : +62-21-2931 5121 FAX : +62-21-2931 5133 / 28 Email : info@dpindo.com	HONG KONG : CHIN LEONG INTERNATIONAL CO LTD LAMERTON ASIA HOLDING LTD TEL : +852-2542 2206 FAX : +852-2544 9563 Email : chinleong@chinleong.com.hk	CHINA: LAMERTON CHEMICAL (SHANGHAI) CO LTD SHANGHAI TEL : +86-21-5830 7559 FAX : +86-21-6840 7408	ZHONG SHAN SOUTH ASIA CHEMICAL LTD ZHONG SHAN TEL : +86-760-8554 4111 FAX : +86-760-8554 4113
--	--	--	---	--	--	--	--	---	---	---	--	--	--