



CL - ENAMEL PAINT

SOLVENT BASED ALKYD HIGH GLOSS ENAMEL PAINT

DESCRIPTION

CL - Enamel Paint is an air dry long oil alkyd based high gloss enamel, suitable for metal and wood substrates as top coat finishing.

FEATURES

- High gloss
- Good adhesion
- Good chemicals resistant
- Ready to use

TECHNICAL PROPERTIES

Density	: Approx. 1.0 kg/l
Viscosity	: Approx. 68 KU
Drying Time	
Touch Dry	: 3 hr @ 30°C
Hard Dry	: 8 hr @ 30°C
Dried Film Thickness	: Approx. 30 microns per coat
Flash point	: 7°C
Thinner	: Turpentine or general purpose thinner

SURFACE PREPARATION

Surface must be sound and clean; free from dirt, dust, grease and other contaminants. If there is loose paint, scrap it off or use water jet to clean. Allowed to dry completely before application.

PRIMING

For metal surface, primed with CL-Red Oxide Primer at the rate of 8 – 10m² per litre. Allow it to dry for at least 6 hours before application.

APPLICATION

Lightly stir the paint before use. Thin with Turpentine or general purpose thinner if needed. Do not add in any filler. Apply by brush or roller or spray at the rate of 8-10 m² per litre per coat. Allow it to dry for at least 8 hours before applying second coat. Avoid contact with rain or water before the paint dry.

PRECAUTION MEASURES

Flammable! Keep away from spark and naked flame. Contain sensitizing solvent. Wear proper PPE e.g. chemical resistant glove, respirator during application. If contact with skin, wash with soap water immediately.

COVERAGE

Approximately 8 - 10 sq meter per litre per coat depending on substrate condition. Minimum 2 coats should be applied.

COLOUR

Available in various colour.

SHELF LIFE

2 years in unopened container.

PACKING

Available in 5 and 20 litre tin.

122014

Disclaimer: Specification are subject to change without notification.

CLP since 1947 HQ/SINGAPORE : CLP INTERNATIONAL PTE LTD CHIN LEONG CONSTRUCTION SYSTEMS PTE LTD TEL : +65-6266 2788 FAX : +65-6266 1240 Email : chinleong@clp.com.sg		MALAYSIA: CLP CONSTRUCTION SYSTEMS SDN BHD SELANGOR TEL : +60-3-3176 5099 FAX : +60-3-3176 2797 Email : clp@clp.com.my		MALACCA TEL : +60-6-263 1677 FAX : +60-6-263 1215	JOHOR TEL : +60-7-252 5385 FAX : +60-7-252 5391	KEDAH TEL : +60-4-489 3066 Fax : +60-4-489 1877	PERAK TEL : +60-5-292 6986 / 6976 FAX : +60-5-292 6936	INDONESIA : PT RANGALO CLP TEL : +62-21-581 3951 FAX : +62-21-581 3950 Email : rangalo@cbn.net.id	PT-CLP INDONESIA TEL : +62-21-2931 5121 FAX : +62-21-2931 5133 / 28 Email : info@clpindo.com
THAILAND: CLPI (THAILAND) CO LTD TEL : +66-2769 5633 FAX : +66-2769 5612 Email : clpi@ksc.th.com	VIETNAM : CLPI VIETNAM CO LTD TEL : +84-8-3526 1033 FAX : +84-8-3526 1032 Email : sales@clp.com.vn	TAIWAN : SIHTACO CO LTD TEL : +886-2-2791 8539 FAX : +886-2-8192 6248 Email : Alice.Lee@sihtaco.com.tw Michael.Ku@sihtaco.com.tw	HONG KONG : CHIN LEONG INTERNATIONAL CO LTD LAMERTON ASIA HOLDING LTD TEL : +852-2542 2206 FAX : +852-2544 9563 Email : chinleong@chinleong.com.hk		CHINA: LAMERTON CHEMICAL (SHANGHAI) CO LTD SHANGHAI TEL : +86-21-5830 7559 FAX : +86-21-6840 7408		ZHONG SHAN SOUTH ASIA CHEMICAL LTD ZHONG SHAN TEL : +86-760-8554 4111 FAX : +86-760-8554 4113		