



CL – KOTE 22AR

ANTI-ROOT ELASTOMERIC WATERPROOFING MEMBRANE COATING

DESCRIPTION

CL-KOTE 22AR is an acrylic based liquid elastomeric coating formulated with anti-root additives to waterproof concrete substrates which require protection against damages from vegetation roots penetration. It is workable for fibrous root system plant, but not for tap root system plant or trees. On installation, CL-Kote 22AR dried up to form a tough, seam free and elastic waterproofing membrane. Roots from plants and vegetation growing towards the CL-Kote 22AR waterproofed concrete structure will be repelled at the coated surface thereby arresting the vegetation roots from further growing into and damaging the concrete structure. CL-Kote 22AR can be applied on concrete, fibrous cement sheet, concrete block, cement render and GRC of planter boxes, roof gardens, landscape terraces and the like. A protective screed is required on top of CL-Kote 22AR prior proceeding to planting.

FEATURES

- Excellent anti-root properties.
- Easy to use. No mixing and dilution are required.
- Excellent adhesion that prevents the spread of water beneath the membrane.
- Forms a complete homogenous waterproofing membrane with no laps, joints or over flashing.

TECHNICAL INFORMATION

Elongation at Break (ASTM D412:2006)	: > 300%
Tensile Strength (ASTM D412:2006)	: > 2.5N/mm ²
Adhesion to Concrete (ASTM D4541:2009)	: > 0.5N/mm ²
Crack Bridging (ASTM C836:2005)	: No crack at 2 mm width
Water Penetration (DIN 1048:Part 5:1991)	: No water penetration @ 0.2kgf/cm ² for 6hr

SURFACE PREPARATION

Surface to be waterproofed must be sound, clean - free of dirt, dust, grease, oil, wax, curing compounds and other contaminants. For cracks, voids, chipped edges, uneven surfaces and holes are to be repaired with CL-Rapid Repair. Fresh concrete must be cured for at least 14 days prior to application.

PRIMER APPLICATION

Apply one coat of CL-Primer P1 to the surface by brush or roller at the rate of 0.15 – 0.2 kg per m². Coverage will vary according to surface profile and porosity of the substrate. Allow it to dry (approx. 20 minutes) before proceeding with CL-Kote 22AR.

Alternatively, CL-Pruf 501 or CL-Pruf 503 is recommended to be used as primer for overcome bubbling problem especially for roof top application. Damp the substrate and apply at the rate of 1.0kg/m² and leave it to dry for at least 8 hours prior membrane application.

APPLICATION

Do not dilute CL-Kote 22AR. Stir CL-Kote 22AR with mechanical mixer at low speed until uniform dispersion prior application. Care should be taken to avoid air trap while stirring. Apply CL-Kote 22AR by brush or roller at the rate of 1kg per m² per coat. Minimum 2 coats to be applied, additional coats are required for thickness buildup. To enhance the strength, it can be reinforced by CL-Fabric. This is done by fully and completely embedding the reinforcing fabric into the first coat when wet and “back rolling” with more coats of CL-Kote 22AR. The reinforcing fabric should be fully saturated with and over coated by the subsequent application of CL-Kote 22AR. Allow to thoroughly dry for a minimum of 2 hours for each coat. Longer time or overnight drying may be necessary in cooler or adverse conditions. Insufficient of drying will cause re-emulsification problem when contact with water. Thereafter, a protective cement sand mortar screed of not less than 25mm shall be installed over the said CL-Kote 22AR waterproofing system.

COLOUR

Light grey.

TOOLS CLEANING

Wash with water immediately after use. Use xylene for partially cured residue.

SHELF LIFE

2 years in an unopened container, stored in cool and dry place.

PACKING

Available in 20kg pail.

112528

Disclaimer: Specification are subject to change without notification.



CLP since 1947
HQ/SINGAPORE : CLP INTERNATIONAL PTE LTD
CHIN LEONG CONSTRUCTION SYSTEMS PTE LTD
TEL : +65-2769 5633
FAX : +65-2769 5612
Email : clp@ksc.th.com

MALAYSIA: CLP CONSTRUCTION SYSTEMS SDN BHD
SELANGOR
TEL : +60-3-3176 5099
FAX : +60-3-3176 2797
Email : clp@clp.com.my

MALACCA
TEL : +60-6-263 0540 /
+60-6-263 1677

JOHOR
TEL : +60-7-252 5385
FAX : +60-7-252 5391

KEDAH
TEL : +60-4-489 3066 /
+60-4-489 3099

PERAK
TEL : +60-5-292 6986 / 6976
FAX : +60-5-292 6936

INDONESIA :
PT RANGALO CLP
TEL : +62-21-581 3951
FAX : +62-21-581 3950
Email : rangalo@cbn.net.id

PT-CLP INDONESIA
ZHONG SHAN
TEL : +62-21-2931 5121
FAX : +62-21-2931 5133 / 28
Email : info@clpindo.com

THAILAND:
CLPI (THAILAND) CO LTD
TEL : +66-2769 5633
FAX : +66-2769 5612
Email : clpi@ksc.th.com

VIETNAM :
CLPI VIETNAM CO LTD
TEL : +84-8-3526 1033
FAX : +84-8-3526 1032
Email : sales@clp.com.vn

TAIWAN :
SIHTACO CO LTD
TEL : +886-2-2791 8539
FAX : +886-2-8192 6248
Email : Alice.Lee@sihtaco.com.tw
Michael.Ku@sihtaco.com.tw

HONG KONG :
CHIN LEONG INTERNATIONAL CO LTD
LAMERTON ASIA HOLDING LTD
TEL : +852-2542 2206
FAX : +852-2544 9563
Email : chinleong@chinleong.com.hk

CHINA:
LAMERTON CHEMICAL (SHANGHAI) CO LTD
SHANGHAI
TEL : +86-21-5830 7559
FAX : +86-21-6840 7408

ZHONG SHAN SOUTH ASIA CHEMICAL LTD
ZHONG SHAN
TEL : +86-760-8554 4111
FAX : +86-760-8554 4113