

CL – KOTE 88

HIGH PERFORMANCE WATER BASED POLYURETHANE ELASTOMERIC WATERPROOFING MEMBRANE COATING

DESCRIPTION

CL-KOTE 88 is a cold applied single component modified polyurethane elastomeric waterproofing system. On installation, it bonds firmly on to the substrate to form a continuous seam-free, tough, elastic, UV resistance and coloured membrane for waterproofing of roofs and balconies as well as various exposed and non-exposed areas. CL-Kote 88 can be applied on concrete, fibrous cement sheet, concrete block, cement render, timber, GRC and metal except aluminum.

FEATURES

- UV resistance.
- Eco-friendly with low VOC.
- No hazardous or toxic substance.
- Easy to use. Mixing and dilution are not required.
- Excellent adhesion with no spread of water beneath the membrane.
- Seamless waterproofing membrane with no laps, joints.
- Can be overlaid with cement screed for non-exposed areas.

CERTIFICATIONS

- Element Singapore
- Sirim Malaysia
- Singapore Green Building Council ✓✓✓✓ Leader
- Singapore HDB approved

TECHNICAL INFORMATION

Elongation at Break (ASTM D412)	500% *
Tensile Strength (ASTM D412)	3N/mm ² *
Adhesion to Concrete (ASTM D4541-02)	> 0.7N/mm ²
Crack Bridging (ASTM C836:C836M-18)	No crack at 2 mm width
Water Penetration (DIN 1048:Part 5:1991)	No water penetration @ 0.7kgf/cm ² for 6hrs

*negative tolerance 20%

SURFACE PREPARATION

Surface to be waterproofed must be sound, clean - free of dirt, dust, grease, oil, wax, curing compounds and other contaminants. All joints should be sealed with suitable flow modulus of walls, floors and wet areas including high performance and paintable joint sealant. All cracks or holes should be repaired with cement mortar or CL-Rapid Repair. Allowed at least 14 days for cement mortar to cure prior application of CL-Kote 88.

PRIMER APPLICATION

For mineral substrate, apply one coat of CL-Primer P1 to the surface by brush or roller at the rate of 0.15 – 0.2 kg per m². Coverage will vary according to surface profile and porosity of the substrate. Allow it to dry (approx. 20 minutes) before proceeding with CL-Kote 88. Alternatively, dilute CL-Kote 88 with water at 25% to 30% and apply as primer at the rate of 0.15 – 0.2kg per m² prior proceeding with CL-Kote 88.

For horizontal mineral substrate, CL-Pruf 501 or CL-Pruf 503 or CL-Pruf 507 is recommended to be used as primer to overcome bubbling problem especially for roof top application. Damp the substrate and apply at the rate of 1.0kg/m² and leave it to dry for at least 8 hours prior membrane application.

For iron metal substrate, it is recommended to use CL-Red Oxide Primer for anti-rust protection. Apply at the rate of 0.1 – 0.13 litre/m² by brush or roller. Allow it to dry completely for at least 8 hours prior membrane application.

APPLICATION

Apply one coat of CL-Kote 88 by brush or roller. To enhance the strength, it can be reinforced by Chopped Strand Mat CS100 or CL-Fabric. This is done by fully and completely embedding the reinforcing fabric by “back rolling” with more CL-Kote 88 when the first coat is still wet. The reinforcing fabric should be fully saturated with and over coated by the second application of CL-Kote 88 membrane. The “back rolling” may use additional material. Allow to thoroughly dry for a minimum of 8 hours before proceeding with further application. Overnight drying may be necessary in cooler or adverse conditions. Apply second coat of CL-Kote 88 and allow to dry. Apply additional coats of CL-Kote 88 membrane if further build-up is required. CL-Kote 88 must be allowed to dry completely prior further application. Insufficient of drying will cause re-emulsification problem when contact with water.

For large area or substrate with various profile, it is recommended to apply by spray. Dilute with 10 - 20% of water before spray.

COVERAGE

- Horizontal substrate: $\sim 1.0 \text{ kg/m}^2/\text{coat}$ @ 2 coats, $\sim 1 \text{ mm}$
- Vertical substrate: $\sim 0.6 \text{ kg/m}^2/\text{coat}$ @ 2 coats, $\sim 0.6 \text{ mm}$

COLOUR

Light grey, dark grey and white. Other colours are available upon request.

TOOLS CLEANING

Wash with water immediately after use. Use xylene for partially cured residue.

SHELF LIFE

2 years in an unopened container, stored in cool and dry place.

PACKING

Available in 20kg pail.

072524



 **CLP since 1947**
HQ/SINGAPORE : CLP INTERNATIONAL PTE LTD
CHIN LEONG CONSTRUCTION SYSTEMS PTE LT
 TEL : +65-6265 2788
 FAX : +65-6265 1240
 Email : chinleong@clp.com.sg

MALAYSIA: CLP CONSTRUCTION SYSTEMS SDN BHD
SELANGOR MALACCA
 TEL : +60-3-3176 5099 TEL : +60-6-263 1677 /
 FAX: +60-3-3176 2797 +60-6-225 0540
 Email : clp@clp.com.my

JOHOR
TEL : +60-7-252 5385
FAX : +60-7-252 5391

KEDAH
TEL : +60-4-489 3066 /
+60-4-489 3099

PERAK
TEL : +60-5-292 6986 / 6976
FAX : +60-5-292 6936

INDONESIA :
PT RANGALO CLP
TEL : +62-21-581 3951
FAX : +62-21-581 3950
Email : rangalo@cbn.net.id

PT-CLP INDONESIA
TEL : +62-21-2931 5121
FAX : +62-21-2931 5133 / 28
Email : info@clpindo.com

THAILAND:
CLPI (THAILAND) CO LTD
TEL : +66-2769 5633
FAX : +66-2769 5612
Email : clpi@ksc.th.com

VIETNAM :
CLPI VIETNAM CO LTD
TEL : +84-8-3526 1033
FAX : +84-8-3526 1032
Email : sales@clp.com.vn

TAIWAN :
SIHTACO CO LTD
TEL : +886-2-2791 8539
FAX : +886-2-8192 6248
Email : Alice.Lee@sihtaco.com.tw
Michael.Ku@sihtaco.com.tw

HONG KONG :
CHIN LEONG INTERNATIONAL CO LTD
LAMERTON ASIA HOLDING LTD
TEL : +852-2542 2206
FAX : +852-2544 9563
Email : chinleong@chinleong.com.hk

CHINA:
LAMERTON CHEMICAL (SHANGHAI) CO LTD
SHANGHAI
TEL :+86-21-5830 7559
FAX : +86-21-6840 7408

ZHONG SHAN SOUTH ASIA CHEMICAL LTD
ZHONG SHAN
TEL : +86-760-8554 4111
FAX : +86-760-8554 4113

Disclaimer: Specification are subject to change without notification.