



CL – PLASTER COAT

GREY / WHITE THIN PLASTER / SKIM COAT

DESCRIPTION

CL – PLASTER COAT is a single component cement based plaster that is designed to cover up pin holes and surface unevenness thereby providing a smooth finishing compared to normal finishes. CL-Plaster Coat comes in four different types; in Base (CL-Plaster Coat PB81) and Finishing (CL-Plaster Coat PF82) coats; and in grey and white colour.

USES

Suitable for plastering on wall and ceiling. Can be applied on concretes, light weight concretes, precast units, rendered surfaces, gypsum boards and the like.

FEATURES

- Good workability
- Superior surface finish.
- Easy to use

TECHNICAL INFORMATION

Description	Base PB81	Finishing PF82
Bulk Density	0.98	0.83
Working Time @25°C	1 – 2 hr	1.5 – 3 hr
Initial Setting Time @25°C	3 hr	3 hr
Final Setting Time @25°C	6 hr	6 hr
Recommended Thickness	2 – 5 mm	1 – 3 mm

SURFACE PREPARATION

Surface of the substrates must be clean, free from dust, dirt, grease, oil, paint, wax, loose contaminant etc. Any major unevenness should be repaired with CL-Rapid Repair or CL-Non Shrink Grout S190. Damp the surface with sprinkle water prior to application.

MIXING

Mix according to the following ratio: -

CL-Plaster Coat PB81 : water = 25 kg : 8.0 – 8.5 litre
40 kg : 13.0 – 13.5 litre

CL-Plaster Coat PF82 : water = 25 kg : 10.0 – 10.5 litre

Measure the desired quantity of water and pour into a suitable size bucket. Pour in the powder while using a mechanical mixer to stir until homogenous pasty slurry is obtained. Allow it to slake for 5 minutes. If a mix should stiffen before application, then it should be discarded. Do not add in water or other ingredients and re-use.

APPLICATION

Apply the mix onto the substrate and lay evenly to the desired thickness. For Base coat, it can be applied up to a thickness of 2 to 5mm in a single application. Thereafter, leave it to dry naturally.

If superior smooth finish is required, apply a further Finishing coat of up to a thickness of 1 to 3mm and leave it to air dry.

COVERAGE

Base Coat PB81 : 1.2 – 1.3 kg/m² @ 1mm thick

Finishing Coat PF82 : 1.1 – 1.2 kg/m² @ 1mm thick

COLOUR

Available in grey and white colour.

SHELF LIFE

12 months in unopened sacks or container, store under cool and dry condition.

PACKING

CL-Plaster Coat PB81 : 25 and 40kg per bag

CL-Plaster Coat PF82 : 25 kg per bag

122010

Disclaimer: Specification are subject to change without notification.



CLP since 1947
HQ/SINGAPORE : CLP INTERNATIONAL PTE LTD
CHIN LEONG CONSTRUCTION SYSTEMS PTE LT
TEL : +66-2769 5633
FAX : +66-2769 5612
Email : chinleong@clp.com.sg

MALAYSIA: CLP CONSTRUCTION SYSTEMS SDN BHD
SELANGOR
TEL : +60-3-3176 5099
FAX : +60-3-3176 2797
Email : clp@clp.com.my

MALACCA
TEL : +60-6-263 1677
FAX : +60-6-263 1215

JOHOR
TEL : +60-7-252 5385
FAX : +60-7-252 5391

KEDAH
TEL : +60-4-489 3066
Fax : +60-4-489 1877

PERAK
TEL : +60-5-292 6986 / 6976
FAX : +60-5-292 6936

INDONESIA :
PT RANGALO CLP
TEL : +62-21-581 3951
FAX : +62-21-581 3950
Email : rangalo@cbn.net.id

PT-CLP INDONESIA
TEL : +62-21-2931 5121
FAX : +62-21-2931 5133 / 28
Email : info@clpindo.com

THAILAND:
CLPI (THAILAND) CO LTD
TEL : +66-2769 5633
FAX : +66-2769 5612
Email : clpi@ksc.th.com

VIETNAM :
CLPI VIETNAM CO LTD
TEL : +84-8-3526 1033
FAX : +84-8-3526 1032
Email : sales@clp.com.vn

TAIWAN :
SIHTACO CO LTD
TEL : +886-2-2791 8539
FAX : +886-2-8192 6248
Email : Alice.Lee@sihtaco.com.tw
Michael.Ku@sihtaco.com.tw

HONG KONG :
CHIN LEONG INTERNATIONAL CO LTD
LAMERTON ASIA HOLDING LTD
TEL : +852-2542 2206
FAX : +852-2544 9563
Email : chinleong@chinleong.com.hk

CHINA:
LAMERTON CHEMICAL (SHANGHAI) CO LTD
SHANGHAI
TEL : +86-21-5830 7559
FAX : +86-21-6840 7408

ZHONG SHAN SOUTH ASIA CHEMICAL LTD
ZHONG SHAN
TEL : +86-760-8554 4111
FAX : +86-760-8554 4113