



CL – PUTTY FLEX PF20

ANTI-MOLD FLEXIBLE REPAIR PUTTY FOR INTERIOR AND EXTERIOR

DESCRIPTION

CL – PUTTY FLEX PF20 a ready to use paintable acrylic based putty designed with smooth and flexibility characteristic that is suitable to repair or fill up gap of crack line or joints of ceiling and wall. It is also formulated for both interior and exterior application with anti-mold function that prevent fungus or mold growth even though not being painted over.

FIXES

Suitable for various substrates like concrete, cement screed, brickwork, gypsum board, cement board, metal, wood, aluminum, PVC etc.

FEATURES

- Can fill hairline crack and up to 5mm width.
- Anti-mold.
- High flexibility that eliminate cracking problem due to movement.
- Superior water resistance.
- Non-shrink.
- UV resistance.
- Easy to apply, no priming required.
- Paintable.
- Interior and exterior application.

TECHNICAL INFORMATION

Appearance	: White viscose paste
Tensile Strength	: > 0.5 N/mm ²
Elongation at Break	: > 150%
Tensile Adhesion Strength	: ≥ 0.5 N/mm ²
Tack Free Time	: Approx. 2 hrs
Drying Time	: 24 hrs

SURFACE PREPARATION

Substrate surface must be cured, dry and clean; free from dust, dirt, oil, grease, loose particles or standing water. For neat finishing requirement, apply masking tape and remove it before the putty skins over.

APPLICATION

Fill up the crack or joints with flexible scrapper or putty knife. Lightly press the scrapper / putty knife over it in order to squeeze the putty into crack line / joints. Smoothen the surface by pulling the scrapper / putty knife along the crack line / joints. Leave the putty to dry overnight prior to next application of painting if required.

PRECAUTION MEASURES

Take care to prevent the surface from water or rain before it becomes film (about 2-3 hours after application).

COVERAGE

Approximately 450cm³ per kg.

SHELF LIFE

2 years in unopened container, stored in cool and dry place.

PACKING

Available in 500g and 5kg pail.

082325

Disclaimer: Specification are subject to change without notification.

CLP since 1947
HQ/SINGAPORE : CLP INTERNATIONAL PTE LTD
CHIN LEONG CONSTRUCTION SYSTEMS PTE LTD
TEL : +65-2769 5633
FAX : +65-2769 5633
Email : chinleong@clp.com.sg

MALAYSIA: CLP CONSTRUCTION SYSTEMS SDN BHD
SELANGOR
TEL : +60-3-3176 5099
FAX : +60-3-3176 2797
Email : clp@clp.com.my

MALACCA
TEL : +60-6-263 1677
FAX : +60-6-263 1215

JOHOR
TEL : +60-7-252 5385
FAX : +60-7-252 5391

KEDAH
TEL : +60-4-489 3066
Fax : +60-4-489 1877

PERAK
TEL : +60-5-292 6986 / 6976
FAX : +60-5-292 6936

INDONESIA :
PT RANGALO CLP
TEL : +62-21-581 3951
FAX : +62-21-581 3950
Email : rangalo@cbn.net.id

PT-CLP INDONESIA
TEL : +62-21-2931 5121
FAX : +62-21-2931 5133 / 28
Email : info@clpindo.com

THAILAND:
CLPI (THAILAND) CO LTD
TEL : +66-2769 5633
FAX : +66-2769 5612
Email : clpi@ksc.th.com

VIETNAM :
CLPI VIETNAM CO LTD
TEL : +84-8-3526 1033
FAX : +84-8-3526 1032
Email : sales@clp.com.vn

TAIWAN :
SIHTACO CO LTD
TEL : +886-2-2791 8539
FAX : +886-2-8192 6248
Email : Alice.Lee@sihtaco.com.tw
Michael.Ku@sihtaco.com.tw

HONG KONG :
CHIN LEONG INTERNATIONAL CO LTD
LAMERTON ASIA HOLDING LTD
TEL : +852-2542 2206
FAX : +852-2544 9563
Email : chinleong@chinleong.com.hk

CHINA:
LAMERTON CHEMICAL (SHANGHAI) CO LTD
SHANGHAI
TEL : +86-21-5830 7559
FAX : +86-21-6840 7408

ZHONG SHAN SOUTH ASIA CHEMICAL LTD
ZHONG SHAN
TEL : +86-760-8554 4111
FAX : +86-760-8554 4113