



CL – WATER PLUG

QUICK SET WATERPROOFING CEMENTITIOUS COMPOUND

DESCRIPTION

CL – WATER PLUG is a quick setting cementitious compound designed to instantly stop running water or seepage leaks from cracks, holes or other openings in masonry or concrete surfaces. Once it is set, it becomes part of the surface to which it is applied.

FEATURES

- Fast setting even at low temperature
- Superior water-stopping power
- No cracking
- Does not corrode metal parts
- Suitable for repairing concrete
- Easy and ready to use


USES

Suitable for use in various concrete structures including tunnels, subways, dam conduits, water and sewage pipes, swimming pools, tanks and also concrete piping joints.

TECHNICAL INFORMATION

Solidify Time : 40 – 60 seconds @ 25°C
 Hardening Time : 50 – 120 seconds @ 25°C
 Compressive Strength : > 15 N/mm² @ 1 day
 > 20 N/mm² @ 3 days

SURFACE PREPARATION



Cut the concrete in “under-cut” shape at the place of leak. Remove any weakened or loose parts adjacent to it and clean the surface with water prior to application of CL-Water Plug.

MIXING RATIO

CL-Water Plug : Water = 5kg : 1.25kg


COVERAGE

5kg of CL-Water Plug will fill approximately 0.03m³ of void area. Minimum thickness applied is 15mm. For filling up of void exceeding 50mm in depth, CL-Water Plug should be applied in layers. Wet each layer before applying the CL-Water Plug.

MIXING

Add CL-Water Plug into water according to ratio and mix quickly using trowel or gloved hand to stiff consistency with no lump. Do not mix more than 30 seconds. Due to its rapid set characteristic, only mix the quantity that can be installed within the hardening time.

INSTALLATION



CL-Water Plug

Shape the mixed CL-Water Plug into a ball and plug into the “under cut” shaped indentation just before it hardened. Apply firm force. Always plug from the outside and working toward the centre of the leak. Level the repaired surface by using trowel before it fully cured.

TOOL CLEANING

Clean the tools and mixing equipment with water immediately after use. Cured material can only be removed mechanically.

SAFETY PRECAUTION

Protective rubber hand glove to be worn when handling CL-Water Plug as strong heat will be generated during the hardening process.

SHELF LIFE

12 months in unopened container, stored under cool and dry condition.

PACKING

Available in :

- 18kg carton (18 bags x 1kg)
- 20kg carton (4 bags x 5kg)
- 5kg tin



052316

Disclaimer: Specification are subject to change without notification.



CLP since 1947
 HQ/SINGAPORE : CLP INTERNATIONAL PTE LTD
 CHIN LEONG CONSTRUCTION SYSTEMS PTE LT
 TEL : +65-6265 2788
 FAX : +65-6265 1240
 Email : chinleong@clp.com.sg

THAILAND:
 CLPI (THAILAND) CO LTD
 TEL : +66-2769 5633
 FAX : +66-2769 5612
 Email : clpi@ksc.th.com

VIETNAM :
 CLPI VIETNAM CO LTD
 TEL : +84-8-3526 1033
 FAX : +84-8-3526 1032
 Email : sales@clp.com.vn

MALAYSIA: CLP CONSTRUCTION SYSTEMS SDN BHD
 SELANGOR MALACCA
 TEL : +60-3-3176 5099 TEL : +60-6-263 1677
 FAX : +60-3-3176 2797 FAX : +60-6-263 1215
 Email : clp@clp.com.my

TAIWAN :
 SIHTACO CO LTD
 TEL : +886-2-2791 8539
 FAX : +886-2-8192 6248
 Email : Alice.Lee@sihtaco.com.tw
 Michael.Ku@sihtaco.com.tw

HONG KONG :
 CHIN LEONG INTERNATIONAL CO LTD
 LAMERTON ASIA HOLDING LTD
 TEL : +852-2542 2206
 FAX : +852-2544 9563
 Email : chinleong@chinleong.com.hk

KEDAH PERAK
 TEL : +60-4-489 3066 TEL : +60-5-292 6986 / 6976
 Fax : +60-4-489 1877 FAX : +60-5-292 6936

CHINA:
 LAMERTON CHEMICAL (SHANGHAI) CO LTD
 SHANGHAI
 TEL : +86-21-5830 7559
 FAX : +86-21-6840 7408

INDONESIA :
 PT RANGALO CLP
 TEL : +62-21-581 3951
 FAX : +62-21-581 3950
 Email : rangalo@cbn.net.id

PT-CLP INDONESIA
 TEL : +62-21-2931 5121
 FAX : +62-21-2931 5133 / 28
 Email : info@clpindo.com

ZHONG SHAN SOUTH ASIA CHEMICAL LTD
 ZHONG SHAN
 TEL : +86-760-8554 4111
 FAX : +86-760-8554 4113